

TECHNICAL DATA SHEET

21/09/2021

N820 OCEAN REC SOLID

COMPOSITION




RECYCLED
NYLON



ELASTANE
High Chlorine
resistance



WEIGHT (±5%)		WIDTH (+3%/-2%)	COURSES	WALES	TOLERANCE FOR COMPOSITION (STANDARD ASTM)
205 g/m ²	308 g/m lin.	150 cm	48/cm	28/cm	±3%

DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135-2015 (1 wash, normal cycle at 41 degree Celsius line dry)	max -5% WIDTH			max -5% LENGTH		
RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD	4 to 4.5					
ULTRAVIOLET PROTECTION FACTOR (U.P. F.) AATCC 183-2010	50+					
STRETCH TO DYNAMOMETER (±15%) ASTM D4964 - LOAD 20 Lbs	88% WIDTH (min 75% - max 101%)			150% LENGTH (min 128% - max 173%)		
MODULUS @ % ELONGATION (30% - 50% - 70%)	30%	50%	70%	30%	50%	70%
	0.4 - 1.0	1.1 - 2.5	3.5 - 9.5	0.4 - 1.0	1.0 - 2.0	2.0 - 3.5
	WIDTH Lbs			WIDTH Lbs		
CARE LABELLING CODES						

SPECIAL RECOMMENDATIONS

WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our products, we reserve the right to modify these when necessary.