

P525 RIYO REC PRINTED



TECHNICAL DATASHEET 25/03/2025

COMPOSITION (ASTM STANDARD ±3% TOLERANCE)		WEIGHT (±5% TOLERANCE)	WIDTH (+3%/-2% TOLERANCE)	COURSES	WALES		
82% RECYCLED POLYESTER	18% ELASTANE HIGH-CHLORINE RESISTANCE	190 g/m ²	148 cm	42 / cm	26 / cm		
		5.6 oz/yd ²	58 inches	107 / inch	66 / inch		
DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135 (1 wash, normal cycle at 41-degree Celsius, tumble dry low)		max -5% WIDTH		max -5% LENGTH			
RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD		4.0 to 4.5					
ULTRAVIOLET PROTECTION FACTOR (U.P.F.) AATCC 183		50+					
PRINTED							
STRETCH TO DYNAMOMETER (±15%) ASTM D4964 - LOAD 20 Lbs		110% WIDTH (min 93% - max 126%)		155% LENGTH (min 132% - max 178%)			
MODULUS @ % ELONGATION (30%-50%-70%)		30%	50%	70%	30%	50%	70%
		0.3 – 0.9	1.1 – 2.3	2.5 – 4.7	0.0 - 0.3	0.4 – 1.4	1.4 – 2.4
		WIDTH Lbs			LENGTH Lbs		
CARE LABELLING CODES							

CERTIFICATIONS



FUNCTIONAL YARNS



SPECIAL RECOMMENDATIONS: WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our product's quality, we reserve the right to modify these data while necessary.