

N112 KIRA REC SOLID + PFP



TECHNICAL DATASHEET 25/03/2025

COMPOSITION (ASTM STANDARD ±3% TOLERANCE)		WEIGHT (±5% TOLERANCE)	WIDTH (+3% / -2% TOLERANCE)	COURSES	WALES						
80% RECYCLED NYLON	20% ELASTANE HIGH-CHLORINE RESISTANCE	190 g/m ²	150 cm	49 / cm	26 / cm						
		5.6 oz/yd ²	59 inches	124 / inch	66 / inch						
DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135 (1 wash, normal cycle at 41-degree Celsius, tumble dry low)			max -5% WIDTH		max -5% LENGTH						
RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD			4.0 to 4.5								
ULTRAVIOLET PROTECTION FACTOR (U.P.F.) AATCC 183			50+								
STRETCH TO DYNAMOMETER (±15%) ASTM D4964 - LOAD 20 Lbs		SOLID			PFP						
		115% WIDTH (min 98% - max 132%)	210% LENGTH (min 179% - max 242%)		105% WIDTH (min 89% - max 121%)	195% LENGTH (min 165% - max 224%)					
MODULUS @ % ELONGATION (30%- 50%- 70%)		30%	50%	70%	30%	50%	70%	30%	50%	70%	
		0.2 - 0.9	0.9 - 1.8	1.8 - 3.6	0.0 - 0.2	0.3 - 1.0	1.0 - 1.6	0.4 - 0.8	1.0 - 2.0	2.3 - 4.3	0.0 - 0.2
CARE LABELLING CODES											

CERTIFICATIONS



CU1004128GRS-2023-00035481



STANDARD 100

21CX00135
CENTRO COT



UPF 50+



FUNCTIONAL YARNS

SPECIAL RECOMMENDATIONS: WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our product's quality, we reserve the right to modify these data while necessary.