

N850 FISHTALE PRINTED



TECHNICAL DATASHEET 25/03/2025

COMPOSITION (ASTM STANDARD ±3% TOLERANCE)		WEIGHT (±5% TOLERANCE)	WIDTH (+3%/-2% TOLERANCE)	COURSES	WALES
80% RECYCLED NYLON	20% RECYCLED ELASTANE HIGH-CHLORINE RESISTANCE	200 g/m ²	143 cm	51/ cm	28/ cm
		5.9 oz/yd ²	56 inches	130/ inch	71/ inch
DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135 (1 wash, normal cycle at 41-degree Celsius, tumble dry low)			max -5% WIDTH	max -5% LENGTH	
RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD			4.5		
ULTRAVIOLET PROTECTION FACTOR (U.P.F.) AATCC 183			50+		
PRINTED					
STRETCH TO DYNAMOMETER (±15%) ASTM D4964 - LOAD 20 Lbs			105% WIDTH (min 89% - max 121%)		170% LENGTH (min 145% - max 196%)
MODULUS @ % ELONGATION (30%-50%-70%)			30%	50%	70%
			0.3-0.8	0.8-1.7	2.5-4.8
			WIDTH Lbs		LENGTH Lbs
CARE LABELLING CODES					

CERTIFICATIONS

FUNCTIONAL YARNS



UPF 50+

SPECIAL RECOMMENDATIONS: WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our product's quality, we reserve the right to modify these data while necessary.