

N920 ECOFIT SENSE SOLID

TECHNICAL DATASHEET 25/03/2025



COMPOSITION (ASTM STANDARD ±3% TOLERANCE)		WEIGHT (±5% TOLERANCE)	WIDTH (+3%/-2% TOLERANCE)	COURSES	WALES
75% RECYCLED NYLON DTY	25% ELASTANE HIGH-CHLORINE RESISTANCE	160 g/m ²	150 cm	53 / cm	29 / cm
		4.7 oz/yd ²	59 inches	135 / inch	74 / inch
DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135 (1 wash, normal cycle at 41-degree Celsius, tumble dry low)			max -5% WIDTH	max -5% LENGTH	
RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD			4.5		
ULTRAVIOLET PROTECTION FACTOR (U.P.F.) AATCC 183			50+		
SOLID					
STRETCH TO DYNAMOMETER (±15%) ASTM D4964 - LOAD 20 Lbs			125% WIDTH (min 106% - max 144%)		215% LENGTH (min 183% - max 247%)
MODULUS @ % ELONGATION (30%-50%-70%)			30%	50%	70%
			0.2-0.6	0.7-1.3	1.3-2.1
			WIDTH Lbs		LENGTH Lbs
CARE LABELLING CODES					

CERTIFICATIONS



CU1004128GRS-2023-00035481



STANDARD 100

21CA00135

CENTROCOT



UPF 50+

SPECIAL RECOMMENDATIONS: WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our product's quality, we reserve the right to modify these data while necessary.