

P365 ATLANTIS REC SOLID + PFP



TECHNICAL DATASHEET 25/03/2025

| COMPOSITION (ASTM STANDARD ±3% TOLERANCE) | | WEIGHT (±5% TOLERANCE) | WIDTH (+3% / -2% TOLERANCE) | COURSES | WALES | | | | | | | | |
|---|---|---|--------------------------------|-----------|--|-----------|-----------|---|-----------|-----------|--|-----------|-----------|
| 78% RECYCLED POLYESTER DTY | 22% ELASTOLEFIN* HIGH-CHLORINE RESISTANCE | 190 g/m ² | 150 cm | 34 / cm | 27 / cm | | | | | | | | |
| | | 5.6 oz/yd ² | 59 inches | 86 / inch | 69 / inch | | | | | | | | |
| DIMENSIONAL CHANGE OF FABRIC AFTER HL AATCC 135 (1 wash, normal cycle at 41-degree Celsius, tumble dry low) | | | max -5% WIDTH | | max -5% LENGTH | | | | | | | | |
| RESISTANCE TO PILLING ASTM D 3512-RANDOM TUMBLE AT 30 MINUTES PHOTOGRAPHIC RATING STD | | | 4.0 to 4.5 | | | | | | | | | | |
| ULTRAVIOLET PROTECTION FACTOR (U.P.F.) AATCC 183 | | | 50+ | | | | | | | | | | |
| STRETCH TO DYNAMOMETER (±15%) ASTM D4964 - LOAD 20 Lbs | | SOLID | | | PFP | | | | | | | | |
| | | 145% WIDTH (min 123% - max 167%) | | | 140% LENGTH (min 119% - max 161%) | | | 130% WIDTH (min 111% - max 150%) | | | 130% LENGTH (min 111% - max 150%) | | |
| MODULUS @ % ELONGATION (30%- 50%- 70%) | | 30% | 50% | 70% | 30% | 50% | 70% | 30% | 50% | 70% | 30% | 50% | 70% |
| | | 0.0 - 0.2 | 0.4 - 1.0 | 1.1 - 2.3 | 0.3 - 0.8 | 1.0 - 2.1 | 2.1 - 3.7 | 0.0 - 0.2 | 0.6 - 1.2 | 1.5 - 2.8 | 0.3 - 0.7 | 1.3 - 2.4 | 2.4 - 4.4 |
| CARE LABELLING CODES | | | | | | | | | | | | | |

CERTIFICATIONS



CU1004128GRS-2023-00035481



STANDARD 100

21CX00135

CENTROCOT



UPF 50+

FUNCTIONAL YARNS



SPECIAL RECOMMENDATIONS: WE RECOMMEND TESTING EACH DYE BATCH BEFORE ANY TREATMENT OR APPLICATION OTHER THAN CUTTING AND SEWING.

To improve our product's quality, we reserve the right to modify these data while necessary.

* Elastolefin **XLANCE**®